



KIRAN WASH PRIMER YELLOW (ETCH PRIMER) (KEP)

A two-pack Etch primer for use on non-ferrous metals. KEP has been designed specially for Passivity the metal and ensuring adhesion to galvanized iron, aluminum, light alloy, etc. This primer may be used in conjunction with other conventional primers.

Typical use of KEP : recommended for use on aluminum cladding, galvanized rails or pipes, metal sprayed steel grating, etc..

Type	Two pack cold cured.
Composition	Special formulated binder with rust in habitue
pigments.	
Mixing ratio	1:1
Pot life	4 hrs after mixing
Apply with	Brush / Roller/Conventional/Airless spray.
Recommended DFT	6 - 8 microns per coat.
Theoretical spreading rate	12.5 - 16.5 sq.mt./ltr..
Drying Time	Touch Dry : 10-15 mins. Dry to handle : 1 hr. Hard dry : 2 hrs.
Overcoating Interval	Minimum 2 hrs.
Flash point	Below 25 oC.
Colour	Yellow.
Packing	40 ltr, 20 ltr., 8 ltr., 4 ltr., 2 ltr., 1 tr..
Finish	Matt.

Storage life : Up to nine months as long as sealed container kept in dry place under normal temperature conditions.

Surface preparation : Non-ferrous metal must be effectively degreased using KIRAN degreasing solvent to ensure adhesion of KEP. Metal spray surface do not require treatment other then stiff brushing and water washing to remove salt and other site Contamination.

Application : Stir each component thoroughly before mixing base and catalyst in equal proportions. Allow maturation time of 10 to 15 minutes and then remix prior to use.



KIRAN PAINTS PVT. LTD.



**THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND
CUSTOMER IS ADVISED TO TEST THE MATERIAL BEFORE USE**

KIRAN PAINTS PVT. LTD.

Factory : Plot No. 48, M.I.D.C., Taloja Ind. Area, Dist. Raigad, Maharashtra-410208, INDIA.
Office : 501, Madhav Apt., Jawahar Road, Ghatkopar (East), Mumbai-400077, INDIA.

Fact. Tel.: 91-22-27410100 Fax: 91-22-27410101
Office Tel.: 91-22-25132776 / 25123780 Fax: 91-22-25154958
Email : sales@kiranpaints.com / dvrkiran@bom3.vsnl.net.in
Website : www.kiranpaints.com